



Quality Wood Finishing Products

# ARMOR VAR ADVANCE

## 9950

### CATALYZED VARNISH

EXTREMELY LOW ODOR \* ULTRA LOW HAPS \* EXTENDED POT LIFE \* WATER WHITE

#### PRODUCT DESCRIPTION

**WOODWRIGHT ARMOR VAR ADVANCE** IS A HIGH BUILD, MODIFIED COCONUT ALKYD CATALYZED VARNISH WITH ATTRACTIVE GRAIN ENHANCING CHARACTERISTICS. IT HAS EXTREMELY LOW ODOR AND MINIMAL EYE & NOSE IRRITATION. THIS PRODUCT CONTAINS LOW HAPS AND VERY LOW VOC. **9950 AV ADVANCE** IS A TRUE HIGH END PERFORMANCE COATING WITH EXCELLENT RESISTANCE TO SCRATCHING, MARRING, MOISTURE AND CHEMICALS. **AV ADVANCE** PROVIDES A GREAT VALUE BY HAVING AN EXTENDED POT-LIFE (WHICH YIELDS VIRTUALLY NO WASTE). THE RESINS SELECTED FOR THIS PRODUCT PROVIDE A CLEAR, WATER WHITE FINISH. AS WITH ALL WOODWRIGHT FINISHES, THIS VARNISH HAS A SILKY FEEL ADDING TO YOUR FURNITURE OR CABINETRY'S QUALITY. **9950 AV ADVANCE** REQUIRES ONLY 4OZ. OF CATALYST PER GALLON AND IS AT A VISCOSITY THAT IS READY TO SPRAY FROM THE CAN. THIS PROVIDES EASE OF APPLICATION AND NO LOSS OF SOLIDS DUE TO THINNING OR A HIGH RATIO OF CATALYST. **9950** CAN BE USED OVER ANY WOODWRIGHT CATALYZED SEALER BUT CAN BE USED AS A SELF-SEAL PRODUCT, AS WELL.

#### PHYSICAL PROPERTIES

|                       |                               |  |
|-----------------------|-------------------------------|--|
| <b>TYPE:</b>          | MODIFIED COCONUT ALKYD        | <b>AIR DRY SCHEDULE W/ 4OZ. CATALYST PER GALLON:</b> |
| <b>V.O.C.:</b>        | 4.56 LB/GAL. (NO H2O)         | <b>TO TOUCH:</b> 20-30 MINUTES                       |
| <b>WEIGHT/GAL.:</b>   | 8.26 LB + OR - 0.15           | <b>TO SAND:</b> 60 MINUTES                           |
| <b>VISCOSITY:</b>     | 25—26 SEC. ZAHN #2 EZ @ 77 F. | <b>TO RECOAT:</b> 60 MINUTES                         |
| <b>SHEENS:</b>        | 20, 35, 45                    | <b>TO PACK:</b> 8 HOURS                              |
| <b>WEIGHT SOLIDS:</b> | 43% + OR - 1%                 |  |
| <b>VOLUME SOLIDS:</b> | 37% + OR - 1%                 |  |

#### APPLICATION

|                    |   |
|--------------------|---|
| <b>METHOD:</b>     | SPRAY, AIRLESS OR AIR ASSISTED (STAINLESS STEEL EQUIPMENT REQUIRED) |
| <b>REDUCER:</b>    | WOODWRIGHT TH2910 LACQUER THINNER OR TH7100 FLOSOL, IF DESIRED      |
| <b>SUBSTRATE:</b>  | WOOD (STAINED IF DESIRED), CLEAN AND DUST FREE                      |
| <b>CATALYST:</b>   | WOODWRIGHT 35260 CATALYST (4OZ. PER GALLON)                         |
| <b>POT LIFE:</b>   | UP TO 48 HOURS @ 77 DEG. F. (SEALED AIRTIGHT)                       |
| <b>SHELF LIFE:</b> | 1YEAR (UNOPENED)  |