



# Reducer Additive Chart

## CONVERSION VARNISH SEALER & TOPCOAT (Use 35260 Catalyst)

Per Gallon Additions	50—59° F	60—69° F	70—79° F	80—89° F	80—89° F High Humidity	90° F +
TH3500 FAST	2—4 OZ	X	X	X	X	X
TH3700 SLOW	X	X	X	2 OZ	2 OZ	3—5 OZ

NOTE: 35260 CATALYST ADJUSTMENT MAY BE NECESSARY WHEN FINISHING OVER DARK/OILY STAINS THAT ARE NOT WOODWRIGHT BRAND. PLEASE CALL 1-800-322-8172 FOR FURTHER INFORMATION.

## 6530 CABINET URETHANE (Use 2200 Urethane Hardener)

Per Gallon Additions	50—59° F	60—69° F	70—79° F	80—89° F	80—89° F High Humidity	90° F +
TH3700 SLOW	X	X	2 OZ	4 OZ	6 OZ	UP TO 8 OZ

## PRECATALYZED VARNISH & LACQUER

Per Gallon Additions	50—59° F	60—69° F	70—79° F	80—89° F	80—89° F High Humidity	90° F +
TH3500 FAST	4—6 OZ	2—4 OZ	X	X	X	X
TH3700 SLOW	X	X	X	2 OZ	4—6 OZ	6—8 OZ

## WOODWRIGHT OIL-BASED STAINS

Per Gallon Additions	50—59° F	60—69° F	70—79° F	80—89° F	80—89° F High Humidity	90° F +
TH3600 MEDIUM	2—4 OZ	X	X	X	X	X
TH3700 SLOW	X	X	X	2—4 OZ	4—6 OZ	6—8 OZ

**ATTENTION: Woodwright brand varnish systems are not to exceed 5 dry mils. Product warranty is void if varnish exceeds 5 dry mils. Please contact your representative if you have questions regarding warranty.**