



QUALITY WOOD FINISHING PRODUCTS

Product Number: 9938

Product Name: Armor Var Elite NF

Type: No-Formaldehyde Catalyzed Varnish

Available Sheens: 5, 10, 20, 35, 45, 60, 90

For proper application instruction please refer to Woodwright's

**"STANDARD STAIN & VARNISH
APPLICATION TECHNIQUE"**

Physical Properties

RESIN:	MODIFIED COCONUT ALKYD	AIR DRY SCHEDULE W/ 4 OZ CATALYST / GAL:
VOC:	4.50 LB/GAL (NO H2O)	TO TOUCH: 30 MIN
WEIGHT:	8.60 LB/GAL (+ OR - 0.15)	TO SAND: 60 MIN
VISCOSITY:	25.00—26.00 SEC / ZAHN #2 EZ @ 77°F	TO RECOAT: 60 MIN
WEIGHT SOLIDS:	42% (+ OR - 1%)	TO PACK: 8 HRS
VOLUME SOLIDS:	37% (+ OR - 1%)	THICKNESS: DO NOT EXCEED 5 DRY MILS TOTAL

Application

METHOD:	SPRAY—AIRLESS OR AIR-ASSISTED (STAINLESS STEEL EQUIPMENT REQUIRED)
REDUCER:	WOODWRIGHT TH2910 THINNER OR TH3700 SLOW REDUCER, IF DESIRED
SUBSTRATE:	WOOD (STAINED, IF DESIRED) CLEAN AND DUST-FREE
CATALYST:	4 OZ PER GALLON WOODWRIGHT 35260 CATALYST
POT LIFE:	UP TO 16HRS @ 77°F (STORED SEALED AND AIRTIGHT)
SHELF LIFE:	1 YEAR UNOPENED
SEALER:	9936 RAPID SEAL ELITE NF SEALER OR SELF-SEAL
FULL CURE:	30 DAYS

Features & Benefits

Woodwright 9938 Armor Var Elite NF has very low odor and virtually no eye and nose burn effect compared to other catalyzed varnishes on the market. A fantastic build in 2 coats. Lays out nicely and hangs well on vertical surfaces. Contains and produces no formaldehyde, which leaves almost no odor during assembly, installation, and upon delivery. Extremely durable against chemicals, heat and moisture after full cure. And, of course, that signature silky Woodwright feel.